

Product information | TECHNICAL DATA SHEET

ZINC 99%.

400 ml, 16.72 Oz, 434 g. NET WT.

GENERAL DESCRIPTION

Pintura de rápido secado muy rica en Zinc, para la protección frente a la corrosión de superficies de hierro y acero. Forma una película relativamente elástica que puede servir como base para otras pinturas. En película seca contiene un 97% de Zinc.

FEATURES

- Excellent anticorrosive potential for cathodic protection.
- Resistant to some chemicals and weathering.
- Excellent adherence.
- Does not contain lead.
- Ultra fast drying.
- High filling power.
- Good covering capability.
- May be used in welding.
- May be used as a primer.

APPLICATIONS

As an undercoat and finish for protection against corrosion of ferrous surfaces in all types of environments through active cathodic protection.

- Structural steel.
- Industrial vehicles.
- Metal fencing.
- Welding joints.
- Metal storage tanks.
- Machinery.
- Metal coastal construction/structures.

Due to its conductive nature, it is suitable for welding processes. Resistant up to 350°C.

INSTRUCTIONS FOR USE

- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- Apply to clean, dry surfaces. Remove corrosion with a wire brush.
- For best results apply in thin layers. Three thin layers are always better than one thick one, and may be repainted within fifteen minutes with the same paint.
- During application it is recommended to shake the spray can periodically.
- Turn the aerosol upside down to clean out the valve after use. If te nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Request safety datasheets.

PHYSICAL PROPERTIES

| | |
|--|--|
| Type of liant: | Epoxiester |
| Color: | Zinc mat |
| Dry to the touch (ASTM D-1640 ISO 1517): | 20'-30' |
| Completely dry (ASTM D-1640 ISO 1517): | 24 h |
| Adherence (ASTM D-3359 ISO 2409): | B |
| Theoretical yield (continuous painting): | 2 m ² for 400 ml |
| Thinner: | Acetato Butilo |
| Product life: | (Well Stored) 5 Years |
| Condition for application: | Minimum room temperature 8°C Surface temperature 5°C a 50°C Max humidity 85% R.H.P |

* Adhesion tests have been carried out on galvanized steel plates.. Last date review: 14/01/2016.

APPARENCE



LABEL



EX0140108 Zinc 99%

PACKAGING

Nominal capacity: 400 ml.
Heat resistance of packaging: <50°C
Propellant: DME

Box (6 units)
205 X 140 X 200 mm.



CAUTION

