

Product information | TECHNICAL DATA SHEET

GALVANIZED ZINC PAINT

400 ml, 10 Oz, 275 g

GENERAL DESCRIPTION

Group of products formulated with fast drying thermoplastic acrylic resins, with zinc powder and / or aluminium.

FEATURES

- Very fast drying.
- Easy to apply and recoat.
- Good adhesion.
- Lead free.
- High covering power.
- Excellent anticorrosive power.

APPLICATIONS

Very suitable for painting all kinds of machinery and iron structures which require handling almost immediately after being painted. Confers a metallic aspect to galvanized surfaces, very suitable for touching up flaws in the parts treated with plating systems, and is also a great coating to be applied on marine and industrial environments.

- Metal structures
- Vehicles
- DIY
- Metallic doors
- Plastics
- Touch-up treatment of metallic structures
- Welding joints

INSTRUCTIONS FOR USE

- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- Apply to clean, dry surfaces. On rusty metallic surfaces, remove rust with a wire brush and prepare an anti-rust primer if considered necessary. Apply an anchor layer on plastics and polyesters.
- For best results apply in thin layers. Three thin layers are always better than one thick one, and may be repainted within ten minutes with the same paint.
- We advise shaking the can during the painting process.
- Turn the aerosol upside down to clean out the valve after use. If the nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Request safety datasheets.

PHYSICAL PROPERTIES


Brinder type:	Thermoplastic acrylic
Color:	Galvanized matte / Gloss
% Zinc (pigments mixture):	Matte 98%, Gloss 66%
Dry to touch (ASTM D-1640 ISO 1517):	5'
Total drying (ASTM D-1640 ISO 1517):	30'
Coat thickness (ASTM D-823 ISO 2808):	25 µ/capa (2coats)
Adherence (ASTM D-3359 ISO 2409):	3B
Salt mist test:	300 h
Theoretical Coverage (continuous painting):	2 m ²
Salt mist test:	300h
Thinner:	Butyl Acetate
Product life:	(Well Stored) 5 years
Recoating:	After 10'
Painted resistance to heat:	300 -350°C
Application conditions:	T° environment 8°C
	T° surface 5-50°C
	Humidity 85% R.H.P.

* Adherence tests were performed on steel.

APPEARANCE



LABEL



CAP SYSTEM



EX0140106	Galvanizada Frio, Zinc Mate 98%	EX0140107	Zinc Brillante Plata Galvanizada	EX0140114	Zinc Claro
-----------	------------------------------------	-----------	-------------------------------------	-----------	------------

PACKAGING

Nominal capacity 400 ml.
Heat resistance of packaging: <50°C
Propellant: GLP C3-C4

Box (6 units)
205 X 140 X 200 mm.



CAUTION

