

## Product information | TECHNICAL DATA SHEET

### STAINLESS PAINT

400 ml, 10 Oz, 270 g.

#### GENERAL DESCRIPTION

Antioxidant coating formulated with acrylic resin and stainless steel metallic pigments. (Stainless Steel).

#### FEATURES

- Excellent anticorrosive power.
- Protects the metallic foundation.
- Lead free.
- Good covering power.
- Very resistant to external temperatures.
- Excellent welding properties.
- High resistance to outdoor exposure.
- Can be recoated with the majority of enamels normally used.
- Ultra-fast drying.
- Good elasticity.

#### APPLICATIONS

As a finish for surface protection of rough stainless steel.

- Structural steel
- Industrial vehicles
- Metallic storage tanks
- Welding joints
- Metallic fences
- Farm Facilities
- Coastal facilities
- All constructions in stainless steel

#### INSTRUCTIONS FOR USE

- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- Apply to clean, dry surfaces. On rusty metallic surfaces, remove rust with a wire brush and prepare an anti-rust primer if considered necessary. Apply an anchor layer on plastics and polyesters.
- For best results apply in thin layers. Three thin layers are always better than one thick one, and may be repainted within ten minutes with the same paint.
- Not suitable in the food industry for surfaces that are in contact with food.
- Turn the aerosol upside down to clean out the valve after use. If te nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Request safety datasheets.

#### PHYSICAL PROPERTIES

Binder type:	Thermoplastic acrylic
Color:	Red stainless steel
Dry to the touch (ASTM D-1640 ISO 1517):	10'
Total drying (ASTM D-1640 ISO 1517):	20'
Thickness of dry layer (ASTM D-823 ISO 2808):	15 µ/capa (2 coats)
Adherence (ASTM D-3359 ISO 2409):	3B
Saline Mist:	300 h
Pigment: Stainless Steel	C<0,03% - Cr 16-18 - Ni 10-14 - Mo 2-3%
Theoretical yield (continuous painting):	2,5 m <sup>2</sup>
Saline Mist:	300h
Thinner:	Butyl Acetate
Product life:	(Well Stored) 5 years
Recoating:	After 10'
Heat resistance of paint:	300°C
Condition for application:	T° environment min 8°C
	T° surface min de 5°C-50°C
	Humidity max 85% R.H.P

\* Adherence tests were performed on steel.

#### IMAGE



#### LABEL



Inoxidable / Stainless Steel  
EX014PRO110

#### CAP SYSTEM



#### PACKAGING

Nominal capacity 400 ml.  
Heat resistance of packaging: <50°C  
Propellant: DME

Box (6 units)  
205 X 140 X 200 mm.

